





100% Combed Cotton S.Jersey  
60 minutes @ 60°  
Test Lot E2685



C.I. NUMBER **Red 141**  
SOLUBILITY **90gr/lt @ 30°**  
INSOLUBILITY **0,50%**  
DISCHARGABILITY **Good**  
Ph VALUE **6,5 - 7,0**



| FASTNESS    |                      |                    |                 |                 |             |
|-------------|----------------------|--------------------|-----------------|-----------------|-------------|
| WASHING     | PERSPIRATION         |                    | RUBBING         |                 | LIGHT       |
| ISO 105-C04 | Alkaline ISO 105-E04 | Acidic ISO 105-E04 | Dry ISO 105/x12 | Wet ISO 105/x12 | ISO 105-B02 |
| 4/5         | 4/5                  | 4/5                | 5               | 4               | 4           |

| SUITABILITY            |         |                |          |            |          |
|------------------------|---------|----------------|----------|------------|----------|
| PROPERTIES             | PROCESS |                |          |            | AFFINITY |
| Chlorinated Pool Water | Exhaust | Cold Pad Batch | Printing | Continuous | Affinity |
| 4                      | HS      | HS             | S        | S          | H        |

HS:Highly Suitable - S:Suitable - NS:Not Suitable    ///    H:High - M:Medium - L:Low

All information given above is according to standarts which were done in our laboratories on above mentioned fabric type and colorant lot. Some values may vary depends on different types of fabrics and colorant lots processed. Liabilities are limited due to usage of all above information without permission. For more information please contact with your local distributour or our website [www.berazol.com](http://www.berazol.com)

