





100% Combed Cotton S.Jersey
60 minutes @ 60°
Test Lot V431



C.I. NUMBER Yellow 145
SOLUBILITY 100gr/lt @ 30°
INSOLUBILITY 0,50%
DISCHARGABILITY Poor
Ph VALUE 6,5 - 7,0



FASTNESS					
WASHING	PERSPIRATION		RUBBING		LIGHT
ISO 105-C04	Alkaline ISO 105-E04	Acidic ISO 105-E04	Dry ISO 105/x12	Wet ISO 105/x12	ISO 105-B02
4/5	4	4	4/5	3/4	4

SUITABILITY					
PROPERTIES	PROCESS				AFFINITY
Chlorinated Pool Water	Exhaust	Cold Pad Batch	Printing	Continuous	Affinity
4/5	HS	HS	S	S	H
<small>HS:Highly Suitable - S:Suitable - NS:Not Suitable /// H:High - M:Medium - L:Low</small>					

All information given above is according to standarts which were done in our laboratories on above mentioned fabric type and colorant lot. Some values may vary depends on different types of fabrics and colorant lots processed. Liabilities are limited due to usage of all above information without permission. For more information please contact with your local distributour or our website www.berazol.com

